

# Perfect Parge

## EIFS Base Coat and Adhesive

### PRODUCT DESCRIPTION

**DuROCK Perfect Parge** is a polymer based dry-mix material that is trowel-applied and used as an adhesive for the attachment of decorative moldings and EPS trim etc. on **DuROCK PUCCS** and **InsulROCK** Systems.

**Perfect Parge** is a flexible and durable base coat that can also be used as a leveling coat for stucco, concrete and masonry substrates. It has excellent freeze-thaw stability, low water absorption, breathable to water vapour and non-combustible. It is a convenient product since it requires only water to be added on site.

### STORAGE & MIXING

Store **Perfect Parge** in a dry place away from direct sunlight. Employ temporary protection measures as needed. **Perfect Parge** cannot be permitted to freeze once it has been mixed with water.

Using a stainless steel or corrosion resistant mixing blade and power drill. Starting with 5.5 L (1.2 gallons) water, gradually add one bag of **Perfect Parge** and mix at 400 – 500 rpm, ensuring not to induce air into the product, until a uniform paste consistency is attained. Let the mixture stand for 5 minutes, then re-mix only **once** before use.

Up to 250 ml (8 oz) of potable water can be added to a full mix of **Perfect Parge** to adjust workability in hot temperature conditions. Accelerators and other additives are prohibited and will void warranty. Discard any material that has begun to stiffen.

### APPLICATION & COVERAGE

Apply **Perfect Parge** with a stainless steel trowel to achieve a minimum dry thickness of at least 1.6 mm ( $\frac{1}{16}$  inch) and embed **DuROCK Fibre Mesh** as per system specifications. Applied as an adhesive, **Perfect Parge** shall be rendered with a notched or standard trowel.

Substrate must be clean, dry, and free of cracks or loose material. Surface and ambient temperatures must be at least 4°C (40°F) a minimum of 24 hours, and must remain so until **Perfect Parge** has cured.

Do not apply **Perfect Parge** in direct sunlight at temperatures exceeding 30°C (86°F) and protect from winds exceeding 25 km/hr (15 mph) as well as precipitation for at least 24 hours.

**Perfect Parge** is available in 22.7 kg (50 lbs) bags, yielding approximately 7.5 m<sup>2</sup> (80 ft<sup>2</sup>) at a nominal thickness of 2.0 mm ( $\frac{1}{12}$  inch).

### TECHNICAL DATA

Technical data available upon request.

Physical Characteristics:

- Non-Sagging
- Tack-free in 2 to 3 hours
- Pot Life – Approx.  $\frac{1}{2}$  to  $\frac{3}{4}$  hour
- Shelf Life – Approx. 3 years
- Cleans up with water

Refer to [www.DuROCK.com](http://www.DuROCK.com) for the most up-to-date version of this document.