

extraflo®

FAST SETTING SELF LEVELLING FLOOR FINISH

PRODUCT DESCRIPTION

ExtraFlo Self Levelling Floor Finish is a redispersible polymer modified cementitious floor coating that is fast setting and finishes to a smooth, non-textured, flat surface. ExtraFlo is designed for use over existing concrete. ExtraFlo is not intended for use over dry pack grouts or mortars. ExtraFlo is grey in colour and is available in 50 lb (22.7 kg) bags.

STORAGE & MIXING

Store ExtraFlo in a dry place away from direct sunlight. Employ temporary protection measures as needed. ExtraFlo cannot be permitted to freeze once it has been mixed with water.

Gradually add one bag of ExtraFlo dry mix to 5 litres of clean, potable water. Using slow mixing action so as not to induce air into the product, mix until a uniform, workable consistency is attained. Over-mixing may cause air bubbles to appear in the finish. Let the mixture stand for five minutes, then remix and use.

APPLICATION & COVERAGE

Make sure the substrate is clean, dry, and free of oil, paint, or any other foreign matter. Allow concrete a minimum of 28 days to cure prior to applying any coating. Non-porous surfaces (such as polished concrete) must be scarified or etched with muriatic acid, thoroughly rinsed and allowed to dry prior to applying any coating. Protect adjacent areas when applying any coating. Clean tools with water before material dries.

Make sure the surface and ambient temperatures are 10°C (50°F) or greater when applying ExtraFlo and remain so until it has fully set and dried (minimum of 24 hours). Prior to the application of ExtraFlo, the substrate must be primed with DuROCK Jewel Prime Coat. Apply ExtraFlo approximately 20 minutes after the application of DuROCK Jewel Prime Coat once the floor becomes tacky.

ExtraFlo can be applied in coats ranging from 1/16 to 2 in. (1.6 to 50 mm). When mixed as per the recommended ratio, one 50 lb (22.7 kg) bag of Extra Flo covers approximately 40 sq ft (3.7 sq m) at ¼ inch (6.4 mm) thickness.